

NEWMAN Sanitary Gasket Company


P.O. BOX 222 • LEBANON, OHIO 45036 • PHONE 513-932-7379 • FAX 513-932-4493

Laboratory Report

PHYSICAL PROPERTIES OF NEWMAN COMPOUND 1108 (Black Buna)

Specific Gravity	1.32 typ
Hardness, Shore "A" pts.	80±2
Ultimate Tensile Strength, psi	1500 min
Elongation, %	250 min
Compression Set, % (Method B, 22 hrs @100°C)	26.2
Operating Temperature, -40°F to 225°F	

Newman Sanitary Gasket Company's Compound 1108 meets the criteria of the FDA, Title 21, Paragraph 177.2600, as a direct contact material with food products, and meets the requirement of NSF 51, used in food equipment.



George Y. Lin
Chief Chemist

November 12, 2009

Filename: LR - 1108.doc
Directory: S:\CustService\Lab Reports
Template: C:\Documents and Settings\larryh\Application
Data\Microsoft\Templates\Normal.dot
Title: NEWMAN Sanitary Gasket Company
Subject:
Author: Newman Sanitary Gasket Company
Keywords:
Comments:
Creation Date: 5/5/2010 8:55 AM
Change Number: 5
Last Saved On: 9/21/2010 8:25 AM
Last Saved By: Rick Schroder
Total Editing Time: 12 Minutes
Last Printed On: 10/18/2010 12:01 PM
As of Last Complete Printing
Number of Pages: 1
Number of Words: 103 (approx.)
Number of Characters: 590 (approx.)