

NEWMAN Sanitary Gasket Company

P.O. BOX 222 • LEBANON, OHIO 45036 • PHONE 513-932-7379 • FAX 513-932-4493

Laboratory Report

PHYSICAL PROPERTIES OF NEWMAN COMPOUND 4137 (RED SILICONE)

Specific Gravity	1.20
Hardness, Shore "A" pts.	73
Ultimate Tensile Strength, psi	1350
Elongation, %	430
300% Modulus, psi	950
Compression Set, % (Method B, 24 hrs @150°C)	33.5

Operating Temperatures: -80°F to 450°F

Newman Sanitary Gasket Company's Compound 4137 meets the criteria of the FDA, Title 21, Paragraph 177.2600 for repeated use in contact with food and also meets the requirements of the 3A Sanitary Standards.

Compound 4137 has also been tested and certified by Toxikon Laboratory to be in compliance with the criteria of the U.S. Pharmacopeia, Class VI Biological Test for Plastics.

George Y. Lin

George Y. Lin
Chief Chemist

4/30/07

Filename: LR - 4137RX.doc
Directory: S:\CustService\Lab Reports
Template: C:\Documents and Settings\larryh\Application
Data\Microsoft\Templates\Normal.dot
Title: NEWMAN Sanitary Gasket Company
Subject:
Author: Newman Sanitary Gasket Company
Keywords:
Comments:
Creation Date: 9/3/2004 11:24 AM
Change Number: 5
Last Saved On: 9/7/2007 9:05 AM
Last Saved By: Preferred Customer
Total Editing Time: 16 Minutes
Last Printed On: 10/18/2010 12:47 PM
As of Last Complete Printing
Number of Pages: 1
Number of Words: 128 (approx.)
Number of Characters: 732 (approx.)