


PERFORMANCE PROPERTY CHART

	FDA			FDA and USP Class VI Compliant						
	Nitrile (Buna-N)	Ethylene-Propylene (EPDM)	Silicone	Fluoroelastomer (Viton™ A) 401C	Fluoroelastomer (Viton™ GF) 600S	Fluoroelastomer (Viton™ ETP) 600S	Teflon®	Silverback™	Kalrez® 6230 & 6221	Kalrez® LS390
Tensile Strength	Good	Good-Excellent	Good	Good-Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
Ozone Resistance	Poor	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
Heat Resistance	Good (225°F) (107°C)	Excellent (275°F) (135°C)	Excellent (450°F) (232°C)	Excellent (450°F) (232°C)	Excellent (450°F) (232°C)	Excellent (450°F) (232°C)	Excellent (450°F) (232°C)	Excellent (450°F) (232°C)	Excellent (500°F) (260°C)	Excellent (428°F) (220°C)
Cold Resistance	Good (-40°F) (-40°C)	Good-Excellent (-55°F) (-48°C)	Excellent (-80°F) (-62°C)	Good (-2°F) (-18°C)	Good (18°F) (-8°C)	Good (10°F) (-12°C)	Excellent (-110°F) (-79°C)	Good (-20°F) (-28°C)	N/A	N/A
Steam Resistance	Good	Excellent	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
Tear Resistance	Good	Good	Good	Good	Good	Good	Excellent	Excellent	Good	Good
Abrasion Resistance	Good	Good-Excellent	Good-Excellent	Good	Excellent	Excellent	Excellent	Excellent	Good	Good
Acid Resistance	Poor-Good	Good-Excellent	Good	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
Base Resistance	Good	Excellent	Good	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
Petroleum Oil Resistance	Excellent	Poor	Good	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
Flame Resistance	Poor	Poor	Poor	Good	Good	Good	Excellent	Excellent	Excellent	Excellent
Vegetable Oil Resistance	Excellent	Good (most)	Good (intermittent)	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent	Excellent
3-A Compliant	Yes	Yes	Yes	Yes	No	No	Yes	No	Yes	No

AUTHORIZED DISTRIBUTOR
DuPont Kalrez
PERFORMANCE ELASTOMER PARTS
"Ask for the Seal You Can Trust"

Buna-N is not recommended for use with CIP Sanitizing Agent OXONIA; use EPDM or Silicone. EPDM or Viton™ is recommended for ozone treated water.



All of the above compounds used in our production meet the criteria set forth by the FDA.



P.O. Box 222, Lebanon, Ohio 45036 • Telephone (513) 932-7379 • Fax (513) 932-4493
www.newmangasket.com e-mail: customer@newmangasket.com

Teflon® is a registered trademark of DuPont and Kalrez is a registered trademark of DuPont Performance Elastomers. Viton™ is a trademark of The Chemours Company FC, LLC, used under license by Newman Sanitary Gasket Company.

© Newman Sanitary Gasket Company. All Rights Reserved. NSG 0418-40 Printed in U.S.A.