

# NEWMAN Sanitary Gasket Company

P.O. BOX 222 • LEBANON, OHIO 45036 • PHONE 513-932-7379 • FAX 513-932-4493

## Laboratory Report

### PHYSICAL PROPERTIES OF NEWMAN COMPOUND 1209 (Black Buna)

Specific Gravity	1.45
Hardness, Shore "A" pts.	85
Ultimate Tensile Strength, psi	1680
Elongation, %	285
200% Modulus, psi	1250
Compression Set, % (Method B, 22 hrs @100°C)	26.5
Operating Temperature, -40°F to 225°F	

Newman Sanitary Gasket Company's Compound 1209 meets the criteria of the FDA, Title 21, Paragraph 177.2600 for repeated use in contact with food.



George Y. Lin  
Chief Chemist

4/30/07

Filename: LR - 1209.doc  
Directory: S:\CustService\Lab Reports  
Template: C:\Documents and Settings\larryh\Application  
Data\Microsoft\Templates\Normal.dot  
Title: NEWMAN Sanitary Gasket Company  
Subject:  
Author: Newman Sanitary Gasket Company  
Keywords:  
Comments:  
Creation Date: 8/19/2007 12:11 PM  
Change Number: 4  
Last Saved On: 8/19/2007 12:50 PM  
Last Saved By: Cindy Swagler  
Total Editing Time: 2 Minutes  
Last Printed On: 10/18/2010 12:08 PM  
As of Last Complete Printing  
Number of Pages: 1  
Number of Words: 94 (approx.)  
Number of Characters: 536 (approx.)