

# NEWMAN Sanitary Gasket Company

P.O. BOX 222 • LEBANON, OHIO 45036 • PHONE 513-932-7379 • FAX 513-932-4493

## Laboratory Report

### PHYSICAL PROPERTIES OF NEWMAN COMPOUND 1135 (Red Buna)

Specific Gravity	1.29
Hardness, Shore "A" pts.	53
Ultimate Tensile Strength, psi	804
Elongation, %	429
300% Modulus, psi	600
Compression Set, % (Method B, 22 hrs @100°C)	27.5
Operating Temperature, -40°F to 225°F	

Newman Sanitary Gasket Company's Compound 1135 meets the criteria of the FDA, Title 21, Paragraph 177.2600 for repeated use in contact with food.

*George Y. Lin*

George Y. Lin  
Chief Chemist

4/30/07

Filename: LR - 1135.doc  
Directory: S:\CustService\Lab Reports  
Template: C:\Documents and Settings\larryh\Application  
Data\Microsoft\Templates\Normal.dot  
Title: NEWMAN Sanitary Gasket Company  
Subject:  
Author: Newman Sanitary Gasket Company  
Keywords:  
Comments:  
Creation Date: 8/19/2007 12:08 PM  
Change Number: 5  
Last Saved On: 10/17/2008 4:59 PM  
Last Saved By: Preferred Customer  
Total Editing Time: 2 Minutes  
Last Printed On: 10/18/2010 12:05 PM  
As of Last Complete Printing  
Number of Pages: 1  
Number of Words: 93 (approx.)  
Number of Characters: 532 (approx.)